



VRUSKHA COMPOSITES

Live Green & Live Happy

NOMEX FIBER FABRIC PROPERTIES

| S.NO | Physical Properties | Range |
|------|---------------------|-----------------------------|
| 1 | Raw Material | Nomex Fiber Fabric |
| 2 | Density | 1.38g/cm ³ |
| 3 | Tenacity | 0.63GPa |
| 4 | Elongation | 30.5-31% |
| 5 | Initial Modulus | 10.8-11.9GPa |
| 6 | Loop Tenacity | 0.5-0.52GPa |
| 7 | Heat Of Combustion | 28.1 * 10 ⁶ J/kg |



VRUKSHA COMPOSITES

Working for Research and Development

Mahatma Gandhi Municipal Market Complex, 1st floor, Plot no. 12,
Amaravathi, Tenali - 522 201, Andhra Pradesh.

E-Mail: vrukshacomposites@outlook.com

Cell: 73586 54515, 7075376577, 9392761152.